

METHOD FOR MANUFACTURING NON-VOLATILE MEMORY

Field of the Invention

5 The present invention relates to a method for manufacturing a non-volatile memory; and, more particularly, a method for manufacturing a non-volatile memory of a SONOS (Silicon-Oxide-Nitride-Oxide-Silicon) structure.

10 Background of the Invention

Conventionally, semiconductor memories are classified into a volatile memory and a non-volatile memory. The volatile memory generally includes a RAM (Random Access
15 Memory) such as a DRAM (Dynamic RAM) or a SRAM (Static RAM). Data may be written and stored in the volatile memory during applying a power supply but the data are volatilized therefrom if a power supply is shut off, thereby losing the data. On the contrary, the non-volatile memory, e.g., a ROM
20 (Read Only Memory) stores data therein even though a power supply is not applied.

Non-volatile memories are divided into floating gate series and MIS (Metal Insulator Semiconductor) series depending on a processing technique. In the MIS, two or
25 more kinds of dielectric films are multi-layered in double or triple layers.

The memory of the floating gate series stores data therein by using a potential well. Such memory of the floating gate series is represented by an ETOX (EEPROM (Electrically erasable programmable read only memory) Tunnel
5 Oxide) structure widely employed as a flash EEPROM.

The memory of the MIS series stores data therein by using traps existing in a dielectric film bulk, an interface between two dielectric films and an interface between a dielectric film and a semiconductor. Such memory of the MIS
10 series is represented by a MONOS/SONOS (Metal ONO Semiconductor/Silicon ONO Semiconductor) structure usually employed as a flash EEPROM.

With the development of the processing techniques, a SOC (System-on-Chip) technique is required and the
15 importance thereof becomes a prominent figure. The SOC technique is referred to techniques capable of performing various functions on a single chip, i.e., basic Logic, SONOS and Flasys. However, such techniques involve too complicated processes.

20

Summary of the Invention

There is, therefore, an object of the present invention to provide a method for manufacturing a non-
25 volatile memory of a SONOS (Silicon-Oxide-Nitride-Oxide-

Silicon) structure, which is capable of generating a logic cell and a flash cell in a substrate at a time, by using a damascene process.

In accordance with the present invention, there is provided a method for manufacturing a non-volatile memory of a SONOS (Silicon-Oxide-Nitride-Oxide-Silicon) structure, including the steps of: depositing an oxide film on a substrate; removing a flash device area and a logic gate area, wherein the flash device area and the logic gate area are areas of the oxide film on which a flash device and a logic gate is to be formed, respectively; stacking a tunnel oxide layer on an opened surface of the substrate corresponding to the area of the oxide film; stacking a first polysilicon over the resultant structure; carrying out a polish with respect to the first polysilicon down to a top surface of the oxide film; removing the oxide film; forming an LDD (lightly doped drain) in an upper portion of the substrate excepting an area occupied by the tunnel oxide layer; depositing a sidewall on a side of the first polysilicon; generating a drain and a source beneath the LDD excepting an area contacted to the sidewall; stacking a TEOS (Tetra Ethyl Ortho Silicate) on the resultant structure excepting the flash device area; depositing an ONO (Oxide-Nitride-Oxide) layer over the resultant structure; stacking a second polysilicon over the ONO layer; carrying out a polish with respect to the second polysilicon and the ONO

layer down to a top surface of the TEOS; and removing the TEOS.

Brief Description of the Drawings

5

The above and other objects and features of the present invention will become apparent from the following description of a preferred embodiment given in conjunction with the accompanying drawings, in which:

10 Figs. 1A to 1J describe cross-sectional views of an object for showing a sequence of processes of manufacturing a non-volatile memory of a SONOS (Silicon-Oxide-Nitride-Oxide-Silicon) structure in accordance with the present invention.

15

Detailed Description of the Preferred Embodiment

Figs. 1A to 1J represent a sequence of processes for manufacturing a non-volatile memory of a SONOS (Silicon-Oxide-Nitride-Oxide-Silicon) structure in accordance with a preferred embodiment of the present invention. In the drawings, a flash structure is constructed on a left portion and a logic area is built on a right portion.

20 Referring to Fig. 1A, an oxide film 12 is deposited on a silicon substrate 10 and an area of the oxide film 12 on which a flash device or a logic gate is to be formed is

25

removed. A thickness of the oxide film 12, which may be adjusted to a gate size but varying depending on a type of a device, is, for example, about 2000 Å to 3000 Å.

5 As shown in Fig. 1B, a tunnel oxide layer 14 is stacked on an opened surface of the silicon substrate 10 where the oxide film 12 is removed. Then a first polysilicon 16 is stacked over the resultant structure. In some cases, an implant is carried out in an area for the flash device, so that a threshold voltage V_t is preferably
10 controlled.

As illustrated in Fig. 1C, a CMP (chemical-mechanical polish) is carried out with respect to the first polysilicon 16 down to a top surface of oxide film 12. Thereafter, the oxide film 12 is etched away by a wet etching.

15 As presented in Fig. 1D, an LDD (lightly doped drain) 18 is formed in an upper portion of the silicon substrate 10 excepting an area occupied by the tunnel oxide layer 14.

As provided in Fig. 1E, a sidewall 20 is deposited on a side of the first polysilicon 16. A source and a drain
20 are generated beneath the LDD 18 excepting an area contacted to the sidewall 20. An oxide film 19 may be formed between the first polysilicon 16 and the sidewall 20 in order that the polysilicon 16 may be protected from being damaged during an implant process for forming a source and a drain.

25 As depicted in Fig. 1F, a TEOS (Tetra Ethyl Ortho Silicate) 22 is stacked on the resultant structure excepting

an area for the flash device.

As represented in Fig. 1G, an ONO (Oxide-Nitride-Oxide) layer 24 is deposited over an entire outer surface of the resultant structure.

5 As explained in Fig. 1H, a second polysilicon 26 for forming a control gate is stacked over the ONO layer 24.

As described in Fig. 1I, a CMP is carried out with respect to the second polysilicon 26 and the ONO layer 24 down to a top surface of the TEOS 22.

10 As seen in Fig. 1J, the TEOS 22 is etched away by a wet etching.

In accordance with the present invention, a damascene process is utilized in manufacturing a non-volatile memory of a SONOS structure; and a logic cell and a flash cell may
15 be generated at a time. Accordingly, pattern processes can be simplified and stably controlled.

While the invention has been shown and described with respect to the preferred embodiments, it will be understood by those skilled in the art that various changes and
20 modifications may be made without departing from the spirit and scope of the invention as defined in the following claims.